

ASTM C 518–04
STEADY-STATE HEAT FLUX
MEASUREMENTS AND THERMAL
TRANSMISSION PROPERTIES BY MEANS OF
THE HEAT FLOW METER APPARATUS

Sealection Agribalance

(1 inch thick)

Project No. 3133593SAT-008

June 30, 2008

Prepared for:

Demilec U.S.A., LLC
2925 Galleria Drive
Arlington, Texas 76011

Intertek Testing Services NA, Inc.
16015 Shady Falls Road
Elmendorf, Texas 78112
Telephone: 210-635-8100 Fax: 1-210-635-8101
e-mail: www.intertek-etlsemko.com

ABSTRACT


Specimens submitted for testing by Demilec U.S.A., LLC and identified as "Sealection Agribalance" were tested in triplicate in accordance with ASTM C 518-04 at 1 inch thick. The samples were tested at a mean temperature of 75 ± 5°F in accordance to AC12. The foam was allowed to age for more than 180 days before testing at 73 ± 5°F.

TEST NO.	HOT & COLD PLATE SEPARATION (mm)	HEAT FLOW ($\frac{W}{m^2}$)	HOT PLATE TEMPERATURE (°C)	COLD PLATE TEMPERATURE (°C)	THERMAL TRANSMISSION ($\frac{W}{m \cdot K}$)	COLD /HOT PLATE DELTA T (°F)
1	25.40	30.17	36.7	12.9	0.0322	42.8
2	25.40	30.11	36.7	12.9	0.0321	42.8
3	25.40	29.92	36.1	12.7	0.0325	42.1
Average	25.40	30.06	36.5	12.8	0.0323	42.6

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

The subject test specimen is a traceable sample selected from the manufacturers facility. Intertek selected the specimen and has verified the composition, manufacturing techniques and quality assurance procedures under its Listing & Follow-up Service program.


This report contains a total of 12 pages.



 Servando Romo
 Project Manager

June 30, 2008

Reviewed and approved:



 Javier Trevino
 Senior Project Engineer

June 30, 2008

TABLE OF CONTENTS

SECTION	PAGE
I. Introduction	4
II. Procedure	6
III. Test Results	7
IV. Conclusions	8
V. Accuracy of the Test Method	10
VI. Appendix	11

I. INTRODUCTION¹

This test method covers the measurement of steady state thermal transmission through flat slab specimens using a heat flow meter apparatus. This is a comparative (or secondary) method of measurement since specimens of known thermal transmission properties must be used to calibrate the apparatus. Properties of the calibration specimens must be traceable to an absolute measurement method, and should be obtained from or traceable to a recognized national standards laboratory. This report was reissued because additional information about the sample selection was added to the report.

The test method is applicable to the measurement of thermal transmission through a wide range of specimen properties and environmental conditions. The method has been used at ambient conditions of 10 to 40°C with thickness up to approximately 250 mm, and with plate temperatures from -195°C to 540°C at 25 mm thickness.

This test method may be used to characterize material properties which may or may not be representative of actual conditions of use. Other test methods such as Test Methods C 236 or C 976 should be used if needed.

To meet the requirements of this test method, the thermal resistance of the sample must be greater than 0.10 K•m²/W in all directions. It is not practical in a test method of this type to try to establish details of construction and procedures to cover all contingencies that might offer difficulties to a person without pertinent technical knowledge. Thus users of this test method shall have sufficient knowledge to satisfactorily fulfill their needs. For example, knowledge of heat transfer principles, low level electrical measurements, and general test procedures is required."

¹ *ASTM C518-04 Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus*, Annual Book of ASTM Standards, 04.06, American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA.

Summary of Test Method

“The heat flow meter apparatus establishes steady state unidirectional heat flux through a test specimen between two parallel plates at constant but different temperatures. By appropriate calibration of the heat flux transducer(s) with calibration standards and by measurement of the plate temperatures and plate separation, Fourier’s law of heat conduction is used to calculate thermal conductivity, thermal resistance, or resistivity.

The accurate use of the test method is limited by the capability of the apparatus to reproduce unidirectional constant heat flux density in the specimens, and by the precision in the measurement of temperature, thickness, EMF produced by the heat flux transducer, etc.

The apparatus shall not be used at temperatures, thickness or resistances, other than those within the range of the calibration, unless it can be shown that there is no difference in accuracy.

The apparatus must be capable of maintaining at least a 10°C temperature difference across the specimen for the duration of the test, unless a smaller LT is a requirement of a particular test. The specimens under test may also limit the use of the test method and these limitations are outlined in Practice C1045.

This evaluation was accomplished using a Model Rapid-k Heat Flow Meter Thermal Conductivity Instrument, manufactured by Dynatech R/D Company. “The Rapid-k determines thermal conductivity in accordance with ASTM C 518 . . .

Heat flow through a solid, results from having a temperature gradient in the material. Thermal conductivity is a material property, which determines how much heat flows through a given thickness of the material when there is a temperature difference. The Fourier linear heat flow equation defines thermal conductivity under steady state conditions as:

$$l = \varnothing \frac{DX}{DT}$$

where:

$$l = \text{thermal conductivity, } \frac{W}{m \cdot K}$$

$$\varnothing = \text{heat flux, } \frac{W}{m^2}$$

DT = temperature difference across distance LX, K

DX = distance between hot and cold plates, m

II. PROCEDURE

“In practice, thermal conductivity determinations are made on thermal insulation by placing a sample of the material between two surfaces maintained at a known temperature. Because of the temperature difference, heat flows through the sample from the hot side to the cold side. The quantity of heat flowing through the sample is measured by a heat flow transducer, which is a device having an output proportional to the heat flow passing through it. This transducer is placed between the sample and the cold plate. Because some heat flows through the edges of the sample to or from the surroundings, the heat flow measurement is made in the central 4 inch square area of a 12 inch square sample only. The heat flow through the central area of the sample is one-directional between the hot and the cold face, as the effect of heat flow across the edges is absorbed entirely by the sample material that surrounds the central heat measuring area.

The Rapid-k test apparatus is used for determining the thermal conductivity of fibrous, cellular, particulate, and other thermal insulation. Although the instrument can be used to test almost any solid insulating materials that can be produced in 12-inch square sections, its primary applications are the testing of coarse grain and non-homogeneous materials, where the large sample is necessary in order to obtain test results that are representative of the sample material in bulk form. Examples are foam plastics, fibrous insulation, sand, asbestos, wood, concrete, and other materials.

Description of Test Specimens

The test specimens were submitted by Demilec U.S.A., LLC and identified as follows:

ID Number: Sealection Agribalance

Description: 1 inch thick - Spray Foam Insulation

Date Received

The samples were received in good condition on 10/26/07.

This Test Witnessed by: N/A

Environmental Conditions: 68°F and 47% r.h.

Three specimens were tested so that an average result could be reported. The specimen was cut into 12 inches by 12 inches by an average thickness of 1 inch and consisted of spray foam insulation. All the specimens were conditioned under standard laboratory conditions ($23 \pm 3^{\circ}\text{C}$ and 50% relative humidity) until they were at constant moisture content, as determined by their attaining constant weight.

Prior to each series of three tests, the Rapid-k was calibrated using a sample whose thermal conductivity is known and traceable to national standards.

To perform the test, the specimen was placed in the Rapid-k instrument, the bottom (cold) plate is brought upwards creating contact of both plates with the test specimen, and the instrument was sealed. The hot and cold plates were then allowed to equilibrate to the required temperatures and their exact temperatures were read from the instrument. In addition, a millivolt signal, which is proportional to the heat flow through the transducer, was recorded.

III. TEST RESULTS

The test results from this evaluation are given in the following table, which contains equilibrium data from each test.

TEST NO.	HOT & COLD PLATE SEPARATION (mm)	HEAT FLOW $\left(\frac{\text{W}}{\text{m}^2}\right)$	HOT PLATE TEMPERATURE ($^{\circ}\text{C}$)	COLD PLATE TEMPERATURE ($^{\circ}\text{C}$)	THERMAL TRANSMISSION $\left(\frac{\text{W}}{\text{m}\cdot\text{K}}\right)$	COLD /HOT PLATE DELTA T ($^{\circ}\text{F}$)
1	25.40	30.17	36.7	12.9	0.0322	42.8
2	25.40	30.11	36.7	12.9	0.0321	42.8
3	25.40	29.92	36.1	12.7	0.0325	42.1
Average	25.40	30.06	36.5	12.8	0.0323	42.6

TEST NO.	DENSITY OF SPECIMEN (kg/m^3)	DURATION OF EQUILIBRIUM PERIOD (min)	DATE TESTED
1	12.15	125.00	6/27/08
2	12.51	145.00	6/27/08
3	13.01	80.00	6/27/08

IV. CONCLUSIONS

The Thermal Conductivity, k , and Thermal Resistance, R , of the specimens tested were:

THERMAL CONDUCTIVITY		
SAMPLE NO.	Btu-in / °F-ft ² -h	W/(m ² K)
1	0.223	0.0322
2	0.223	0.0321
3	0.225	0.0325
Average	0.224	0.0323

Thermal resistance ($R, \frac{K \cdot m^2}{W}$) is a function of thickness, and is determined by dividing the thickness in meters by the thermal conductivity.

The table below gives the average thermal resistance for a range of practical thicknesses, in both SI and English units:

R-VALUE			
THICKNESS (in.)	THICKNESS (mm)	R (K·M ² /W)	R (°F·ft ² ·h/Btu)
1.00*	25.4	0.787	4.47
2.00	50.8	1.574	8.94
3.00	76.2	2.361	13.41
3.50	88.9	2.755	15.64
4.00	101.6	3.149	17.88
6.00	152.4	4.723	26.82

Note: These results are based on the average thermal transmission of all three samples.

* This is the average tested thickness of 3 samples.

COLD & HOT PLATE MEAN TEMPERATURES		
SAMPLE NO.	MEAN TEMP. °F	MEAN TEMP. °C
1	76.6	24.8
2	76.6	24.8
3	75.9	24.4
Average	76.4	24.7

The tables below illustrate the constants to convert from standard SI units to any of the other commonly used units. To convert from any set of units in the left-most column to any of the sets of units along the top row, multiply by the constant in the intersecting square:

THERMAL CONDUCTIVITY, I (SI Units = $\frac{W}{m \cdot K}$)

	$\frac{W}{m \cdot K}$	$\frac{W}{cm \cdot K}$	$\frac{cal}{s \cdot cm \cdot K}$	$\frac{kg \cdot cal}{h \cdot m \cdot K}$	$\frac{Btu}{h \cdot ft \cdot ^\circ F}$	$\frac{Btu \cdot in}{h \cdot ft^2 \cdot ^\circ F}$
$\frac{W}{m \cdot K}$	1	1×10^{-2}	2.388×10^{-3}	0.8598	0.5778	6.933
$\frac{W}{cm \cdot K}$	100	1	0.2388	85.98	57.78	693.3
$\frac{cal}{s \cdot cm \cdot K}$	418.7	4.187	1	360	241.9	2903
$\frac{kg \cdot cal}{h \cdot m \cdot K}$	1.163	1.163×10^{-2}	2.778×10^{-3}	1	0.672	8.064
$\frac{Btu}{h \cdot ft \cdot ^\circ F}$	1.731	1.731×10^{-2}	4.134×10^{-3}	1.488	1	12
$\frac{Btu \cdot in}{h \cdot ft^2 \cdot ^\circ F}$	0.1442	1.442×10^{-3}	3.445×10^{-4}	0.124	8.333×10^{-2}	1

THERMAL RESISTANCE, R (SI UNITS = $\frac{K \cdot m^2}{W}$)

	$\frac{K \cdot m^2}{W}$	$\frac{K \cdot cm^2}{W}$	$\frac{K \cdot cm^2 \cdot s}{cal}$	$\frac{K \cdot m^2 \cdot h}{kg \cdot cal}$	$\frac{^{\circ}F \cdot ft^2 \cdot h}{Btu}$
$\frac{K \cdot m^2}{W}$	1	1×10^4	4.187×10^4	1.163	5.678
$\frac{K \cdot cm^2}{W}$	1×10^{-4}	1	4.187	1.163×10^{-4}	5.678×10^{-4}
$\frac{K \cdot cm^2 \cdot s}{cal}$	2.388×10^{-5}	0.2388	1	2.778×10^{-5}	1.356×10^{-4}
$\frac{K \cdot m^2 \cdot h}{kg \cdot cal}$	0.8598	8.598×10^3	3.6×10^4	1	4.882
$\frac{^{\circ}F \cdot ft^2 \cdot h}{Btu}$	0.1761	1.761×10^3	7.373×10^3	0.2048	1

V. UNCERTAINTY OF METHOD

The uncertainty of the Rapid-k apparatus is estimated to be 4% at the two standard deviation level.

APPENDIX

Additional Sample Information

Additional information about the sample

Sealection Agribalance is two part spray-applied, semi-rigid open-cell polyurethane foam insulation with density of 0.7 pcf

Preparation of the samples was witnessed by Intertek Testing Services inspector at the Demilec, USA, LLC. manufacturing facility, located at 2925 Galleria Drive, Arlington, TX 76011 on October 18 and 19, 2007. Samples were received at the Evaluation Center on October 26, 2007 in good condition.

The inspector witnessed preparation of the B-side (resin Sealection Agribalance) batch, verified its composition and randomly selected A-side (isocyanate A 500) from the manufacturing facility. Further, he witnessed the application of the final product, Sealection Agribalance foam, and marked the sprayed foam samples appropriately.

The samples provided by the client were sprayed to the thickness of 3.0 - 6.0 inches. After conditioning, samples were cut into dimensions 12 inches by 12 inches by a thickness of 1 inch.